



GinShiCel MH256C

Technical Data Sheet

Product description

It is a medium to high viscosity grade of hydroxypropyl methyl cellulose ether, which builds up viscosity quickly. Mainly used in all kinds of repair mortar, plastering/masonry mortar, tile adhesive, interior and exterior wall putty, decorative mortar, gypsum-based mortar and other fields.

Performance

Give the mortar excellent suspension function, anti-settling, no bleeding
Ensures proper consistency of mortar with excellent workability and operating time
It has good wettability, so that the mortar and the bottom layer are fully bonded
Provides excellent water retention properties and reduces mortar shrinkage

Product index

Appearance: white or off-white powder
Viscosity (BK, 2%, 20°C)/mpa·s: 45000-50000
Ash/%: ≤5.0
Sieve residue (180μm standard sieve)/%: ≤8.0

Package specification

Composite woven bag lined with plastic film or kraft paper, 25kg/bag.

Storage and transportation

Storage and transportation should be carried out in a cool and dry place, sealed and packaged.
The product is susceptible to moisture. In the case of high temperature and high humidity, it is necessary to prevent moisture and pressure to avoid agglomeration or caking.
If the product is not used up, the packaging must be tightly sealed to prevent the intrusion of moisture.

Shelf life

It can be stored for 2 year under the condition of storage and transportation.If the product exceeds the shelf life, it can only be used after testing and verification.

Note: All the data and suggestions provided above are our reference opinions based on our understanding of current raw materials and applied technology, Since the quality of raw materials, production process, actual construction requirements and use environment adopted by users cannot be controlled, our company does not imply any guarantee and commitment to the quality of users' end products! The user is responsible for the adjustment of the formula system and the final control of quality according to the actual situation.