Zhejiang Haishen New Materials Limited No.5 Yuzhou Road, Lihai Street, Yuecheng District, Shaoxing City, Zhejiang Province

Haishen

aishen

Haisher

T:+86 575 82780578 www.ginshicel.com

faisher

Haishen

Haishen



GinShiCel HE37-S-P **Technical Data Sheet**

Product description

It is a kind of hydroxyethyl cellulose ether with medium viscosity grade, which can delay the dissolution in water to form a clear solution. It is mainly used for dry powder art coatings, such as micro-cement and inorganic coatings, texture coatings, such as real stone paint and color coatings, and one-component or two-component liquid building materials, such as latex paint.

Performance

It can quickly disperse in water without clumping, and the sticking time can be determined according to needs

Obvious thickening effect, good acid and alkali resistance, strong salt resistance Excellent water retention and moisturizing properties and good lubricity

It has good compatibility with various surfactants, stable emulsification and mild solution.

Appearance: white or off-white powder Viscosity (BK, 1%, 25°C)/mpa s:1300-1700 Ash/%: ≤7.0

Sieve residue (180µm standard sieve)/%: ≤8.0

Package specification Composite woven bag lined with plastic film or kraft paper, 25kg/bag.

Storage and transportation Storage and transportation should be carried out in a cool and dry place, sealed and

The product is susceptible to moisture. In the case of high temperature and high humidity, it is necessary to prevent moisture and pressure to avoid agglomeration or

If the product is not used up, the packaging must be tightly sealed to prevent the intrusion of moisture.

Shelf life

It can be stored for 2 year under the condition of storage and transportation. If the product exceeds the shelf life, it can only be used after testing and verification.

Note: All the data and suggestions provided above are our reference opinions based on our understanding of current raw materials and applied technology, Since the quality of raw materials, production process, actual construction requirements and use environment adopted by users cannot be controlled, our company does not imply any guarantee and commitment to the quality of users' end products! The user is responsible for the adjustment of the formula system and the final control of quality according to the actual situation.