



GinShiCel ME64

Technical Data Sheet

Product description	It is a medium viscosity grade hydroxyethyl methyl cellulose ether for fast adhesion. Mainly used in all kinds of repair mortar, plastering/masonry mortar, tile glue, inner and outer wall putty, decorative mortar, gypsum based mortar and other fields.
Performance	Endows mortar with excellent suspension function, anti settlement, no bleeding. Ensure proper consistency of mortar, with excellent operability and operation time. It has good wettability, so that the mortar and the bottom layer are fully bonded. It can be used in high temperature environment to provide excellent water retention and reduce the shrinkage of mortar.
Product index	Appearance: white or almost white powder Viscosity (BK, 2%, 20°C)/mpa·s: 20000-24000 Ash content /% : ≤5.0 Screen residue (180μm standard screen)/% : ≤8.0
Package specification	Composite woven bag lined with plastic film or kraft paper, 25kg/bag.
Storage and transportation	Storage and transportation should be carried out in a cool and dry place, sealed and packaged. The product is susceptible to moisture. In the case of high temperature and high humidity, it is necessary to prevent moisture and pressure to avoid agglomeration or caking. If the product is not used up, the packaging must be tightly sealed to prevent the intrusion of moisture.
Shelf life	It can be stored for 2 year under the condition of storage and transportation. If the product exceeds the shelf life, it can only be used after testing and verification.

Note: All the data and suggestions provided above are our reference opinions based on our understanding of current raw materials and applied technology. Since the quality of raw materials, production process, actual construction requirements and use environment adopted by users cannot be controlled, our company does not imply any guarantee and commitment to the quality of users' end products! The user is responsible for the adjustment of the formula system and the final control of quality according to the actual situation.