

Zhejiang Haishen New Materials Limited
No.5 Yuzhou Road, Lihai Street,Yuecheng District, Shaoxing City,Zhejiang Province

T:+86 575 82780578
www.ginshicel.com



GinShiCel ME96-SD-P

Technical Data Sheet

Product description	It is a medium viscosity hydroxyethyl methyl cellulose ether, which can delay the formation of a transparent solution in water. It is mainly used in the field of stone coating, color coating and other texture coating, latex paint and other single or two component liquid building materials coating.
Performance	It can quickly disperse in water without clumping. Different bonding time can improve the intersolubility of excipients With good wettability, improve the adhesion between the base Provide excellent water retention performance to ensure full operation time Thickening effect is obvious, giving excellent suspension function, anti settlement, no stratification With good thixotropy and leveling, anti splash, anti flow hang, improve construction Can work under high temperature link
Product index	Appearance: white or almost white powder Viscosity (BK,2%,20°C)/mpa·s: 27000-33000 Ash content /% : ≤5.0 Screen residue (180µm standard screen)/% : ≤8.0
Package specification	Composite woven bag lined with plastic film or kraft paper, 25kg/bag.
Storage and transportation	Storage and transportation should be carried out in a cool and dry place, sealed and packaged. The product is susceptible to moisture. In the case of high temperature and high humidity, it is necessary to prevent moisture and pressure to avoid agglomeration or caking. If the product is not used up, the packaging must be tightly sealed to prevent the intrusion of moisture.
Shelf life	It can be stored for 2 year under the condition of storage and transportation.If the product exceeds the shelf life, it can only be used after testing and verification.

Note: All the data and suggestions provided above are our reference opinions based on our understanding of current raw materials and applied technology, Since the quality of raw materials, production process, actual construction requirements and use environment adopted by users cannot be controlled, our company does not imply any guarantee and commitment to the quality of users' end products! The user is responsible for the adjustment of the formula system and the final control of quality according to the actual situation.